

1 Postscript figure is found at XXX.

Existence of the LOFF State in Superconducting UPd_2Al_3

M. R. Norman

*Materials Science Division
Argonne National Laboratory
Argonne, IL 60439*

PACS numbers: 74.20.-z, 74.70.Tx

In a recent Letter, Gloos et al¹ have suggested that the heavy fermion superconductor, UPd_2Al_3 , has a transition in magnetic field from the normal state to an inhomogeneous superconducting state, known as the LOFF state², followed at lower fields by a first order phase transition to the usual flux lattice state. To investigate this, the author derives a formula for the upper critical field for the LOFF state valid at all temperatures in the clean limit (the previous work of Gruenberg and Gunther was restricted to zero temperature³), and shows that the LOFF state cannot quantitatively explain the phase diagram for UPd_2Al_3 . This indicates that a more general solution which breaks cylindrical symmetry is necessary to explain the data.

The derivation of H_{c2} follows that of WHH⁴ (the author notes that the alteration of the H_{c2} equations to incorporate a LOFF state as suggested in the WHH paper is not correct). The LOFF state is obtained by multiplying the usual eigenvector of the Gor'kov equations at H_{c2} by e^{iQz} . Following the same procedure as WHH, the T_c equation is

$$\ln\left(\frac{T_{c0}}{T_c}\right) = 2 \sum_{n=0}^{\infty} \left[\frac{1}{2n+1} - \text{Re}(I_n) \right] \quad (1)$$

where

$$I_n = \frac{2\pi T_c}{\sqrt{E_F \hbar \omega_c}} \int_{\eta}^{\infty} dw e^{-w^2 + \eta^2} \frac{1}{2i} \ln\left(\frac{1 + i\alpha_n w}{1 - i\alpha_n w}\right) \quad (2)$$

and $\alpha_n = \frac{\sqrt{E_F \hbar \omega_c}}{\omega_n + id}$ with E_F the Fermi energy, $\hbar \omega_c$ the cyclotron frequency, $\omega_n = (2n + 1)\pi T_c$, $d = \frac{q}{4} \hbar \omega_c \frac{m^*}{m}$, and g is the g factor. The quantity η is $Q \sqrt{\frac{\hbar c}{2eH}}$. The results of these equations match the zero temperature curves presented by Gruenberg and Gunther³ (the author notes that Eq. 10 of that paper does not appear to be written down correctly).

The parameters used for UPd_2Al_3 are $T_{c0}=2$ K, $E_F=180$ K, $g=2$, and $m^*=37$ (only the ratio E_F/m^* enters the equations). This yields an upper critical field slope at zero field of 4.2 T/K consistent with experimental data¹. Fig. 1 shows the low temperature behavior of H_{c2} for both zero Q and non-zero Q . The zero temperature H_{c2} is considerably lower than the experimental value of 3.5 T. Moreover, the LOFF state does not exist for $T > 0.3$ K, whereas the experimental phase lines are split up to $T = 1.7$ K. One can increase H_{c2} by decreasing the g factor (note, the conduction electrons are relativistic in this case, so the g factor can differ significantly from 2), but this leads to a rapid suppression of the LOFF state (a g of 1.5 gives an H_{c2} of 3.5 T, but no LOFF state). Another approach is to increase T_{c0} as suggested by Gloos et al¹, the idea being that the actual T_c at zero field is somewhat suppressed over its bare value by pair breaking from the antiferromagnetism. This is demonstrated by the other set of curves in Fig. 1, where a T_{c0} of 2.3 K is used. Although these curves are improved over the previous set, the LOFF state does not exist for $T > 0.5$ K, compared to the experimental value of 1.7 K.

Although the author believes that the physical scenario put forth in Ref. 1 is reasonable, it appears that the LOFF state is too restrictive to explain the data. If one generalizes Q to a vector, then one of the form (Q_x, iQ_x, Q_z) also satisfies Eq. 1, but with the same T_c . Thus, to do better than this, one must break cylindrical symmetry (this is likely caused by the antiferromagnetism, as suggested in Ref. 1). In that case, though, the Abrikosov solution is no longer valid. To obtain the more general solution would require rederiving Eq. 1 with a spatially dependent field, a challenging problem which hopefully will be taken up in the future.

This work was supported by U.S. Department of Energy, Office of Basic Energy Sciences, under Contract No. W-31-109-ENG-38.

REFERENCES

1. K. Gloos et al, *Phys. Rev. Lett.* **70**, 501 (1993).
2. P. Fulde and R. A. Ferrell, *Phys. Rev.* **135**, A550 (1964); A. I. Larkin and Y. N. Ovchinnikov, *Zh. Eksp. Teor. Fiz.* **47**, 1136 (1964).
3. L. W. Gruenberg and L. Gunther, *Phys. Rev. Lett.* **16**, 996 (1966).
4. N. R. Werthamer, E. Helfand, P. C. Hohenberg, *Phys. Rev.* **147**, 295 (1966).

FIGURE CAPTIONS

1. Calculated H_{c2} vs. T for UPd_2Al_3 . The lower set of curves is for $T_{c0}=2$ K, the upper set for $T_{c0}=2.3$ K.